

DEGUSSIT® AL24

February 2025

Material Type: Alumina (α -Al₂O₃)

MECHANICAL AND PHYSICAL PROPERTIES OF THE MATERIAL (TYP.)

Characteristic	Standard	Specification	Unit	Value
Content			[%]	> 99.5
Density (ρ_b)	DIN EN ISO 18754		[g/cm ³]	> 3.40
Open (apparent) porosity (π_a)	DIN EN ISO 18754		[vol-%]	≤ 12
Average size of crystallites (g_{mli})	ISO 13383-1	A1	[μm]	40
Flexural strength ($\sigma_{f,4}$)	DIN EN 843-1	Four-Point-Bending	[MPa]	150
Compressive strength ($\sigma_{c,m}$)	DIN ISO 17162		[MPa]	1000
Maximum service temperature (T_{max})		in air	[°C]	1950
Mean coefficient of linear thermal expansion ($\bar{\alpha}$)	DIN EN ISO 17562	20 - 1000 °C	[10 ⁻⁶ /K]	8.2
Specific heat capacity (c_p)	DIN EN 821-3	20 °C	[J/(kg·K)]	900
Thermal conductivity (λ)	DIN EN ISO 18755	20 °C	[W/m·K]	27.8
		1000 °C		5.5
		1500 °C		4.5
Typical colour			[-]	creme white

The preliminary remark in DIN 60672-2 applies analogously to the property values given in the table, according to which the reported values apply only to the test specimens on which they were determined. Assignment to other forms is therefore only conditional permissible. The reference values given are to be understood as such. They refer to a temperature of 20 °C, unless otherwise stated.